

KESTAMİD® RODS

Nominal Diameter mm	Real Diameter mm	Weight Gr/Piece	
		Nominal Lenght 500 mm	Nominal Lenght 1000 mm
15	17.4	149	
20	22.4	246	
25	27.4	368	
30	32.4	514	
35	37.4	685	
40	42.4	880	
45	47.4	1,100	
50	52.4	1,344	
55	57.4	1,613	
60	62.4	1,906	3,726
65	67.4	2,223	4,348
70	72.4	2,565	5,016
75	77.4	2,932	5,733
80	82.4	3,323	6,498
85	87.4	3,738	7,310
90	92.4	4,178	8,170
95	97.4	4,642	9,079
100	102.4	5,131	10,034
105	108.0	5,708	11,162
110	113.0	6,248	12,219
115	118.0	6,813	13,325
120	123.0	7,403	14,478
125	128.0	8,017	15,679
130	133.0	8,656	16,927
135	138.0	9,319	18,224
140	143.0	10,006	19,568
145	148.0	10,718	20,961
150	153.0	11,454	22,401
160	164.2	13,193	25,800
170	172.4	14,543	28,442
180	182.4	16,279	31,837
190	192.4	18,113	35,423
200	202.4	20,045	39,201
210	217.2	23,083	45,144
220	222.4	24,202	47,331
230	232.4	26,427	51,683
240	242.4	28,750	56,227
250	252.4	31,171	60,961
260	262.4	33,690	65,888
270	272.4	36,307	71,005
275	277.4	37,652	73,636
280	282.4	39,021	76,314

TOLERANCES	
Diameter mm	Tolerance mm
15 - 100	+0, +4
101 - 150	+1, +5
151 - 200	+1, +7
201 - 355	+1, +12
356 - 500	+1, +15
501 - 700	+1, +30

LENGHT TOLERANCES	
Lenght mm	Tolerance mm
500	+0, +70
1000	+0, +100

On request, it can be produced in different dimensions.

KESTAMİD® RODS

Page: 2/2

Nominal Diameter mm	Real Diameter mm	Weight Gr/Piece	
		Nominal Length 500 mm	Nominal Length 1000 mm
300	307.2	46,176	
310	317.2	49,231	
315	322.2	50,795	
325	332.2	53,997	
340	347.2	58,983	
355	362.2	64,190	
375	384.0	72,149	
400	409.0	81,850	
410	419.0	85,901	
430	439.0	94,297	
450	459.0	103,085	
500	509.0	126,766	
625	643.0	202,297	
670	688.0	231,603	
700	718.0	252,241	

Kestamid® Polikim's registered trademark

TOLERANCES	
Diameter mm	Tolerance mm
15 - 100	+0, +4
101 - 150	+1, +5
151 - 200	+1, +7
201 - 355	+1, +12
356 - 500	+1, +15
501 - 700	+1, +30

LENGHT TOLERANCES	
Lenght mm	Tolerance mm
500	+0, +70
1000	+0, +100

On request, it can be produced in different dimensions.